

Technical Datasheet

ISOMAT PROFESSIONAL ACRYL

Acrylic paint for exterior use, ideal for professionals

Description

ISOMAT PROFESSIONAL ACRYL is a matt acrylic paint for exterior use, ideal for professionals. Suitable for new or old surfaces requiring frequent painting, such as in public buildings, hotels, hospitals, schools, etc., as well as surfaces stained with graffiti. Features high opacity and surface coverage while offering great workability and flow. Has high resistance to weather conditions and aging, as well as quick-drying and recoat times. Offers a beautiful matt finish.

Fields of application

ISOMAT PROFESSIONAL ACRYL is used for indoor or outdoor applications, on new or old surfaces, on substrates such as concrete, plaster, bricks, gypsum boards, asbestos cement, wood, on surfaces puttied with acrylic or cementitious putties, etc.

Technical data

Colors:	white and thousands of colors (ISOMAT COLOR SYSTEM)
Type:	acrylic paint
Volume solids:	40 ± 2%
Dry film thickness: (EN ISO 2808)	30 ± 2 µm
Wet film thickness: (EN ISO 2808):	68 ± 5 µm
Viscosity: (EN ISO 2884- 2)	115 ± 5 KU
Density (WHITE): (EN ISO 2811- 1)	1.44 ± 0.03 kg/l
pH: (EN ISO 4316)	8-9.5
Adhesion: (EN ISO 4624)	≥ 2.25 N/mm ²
Vapor permeability: (EN ISO 7783- 2: V ₁ high, < 0.14)	Sd= 0.06±0.02 m

Capillary water absorption: (EN ISO 1062- 3: W ₃ low, w< 0.10 Kg/m ² h ^{0.5})	0,07 ± 0,02kg/m ² .h ^{0.5}
Drying time: (EN ISO 9117)	~ 1 h (touch dry)
Recoat time: (EN ISO 9117)	3-4 h
VOC content:	15.8 g/l

Measurements acc. EN 13300

Gloss level: (EN ISO 2813: < 10 at 85°)	Matt
Hiding power (Opacity): (EN ISO 6504- 3)	≥90%
Whiteness: (EN ISO 6504- 3)	≥ 86%
Wet Scrub Resistance: (EN ISO 11998: ≥ 5 µm & < 20 µm, at 200 wash cycles)	CLASS II

Cleaning of tools:

Remove as much paint as possible from the used tools, before cleaning. Clean the tools thoroughly with water and detergent, immediately after use.

Directions for use

1. Substrate preparation

The substrate should be dry and free of grease, loose particles, dust etc.

- Cracks or joints are filled with ISOMASTIC-A acrylic sealant.
- Any imperfections in concrete should be patched with DUOCRET polymer-modified mortar, while imperfections in exposed concrete should be treated with PLANFIX or PLANFIX-FINE polymer-modified putties.
- Plastered wall may be patched with UNICRET and UNICRET-FAST premixed mortars.

The substrate should be primed with the silicone acrylic, micronized, water-based primer PRIMER ACRYL, thinned up to 50% with clean water or with PRIMER ACRYL-S acrylic, solvent-based primer, thinned up to 100% with SM-18 of ISOMAT or with WHITE SPIRIT.

ISOMAT PROFESSIONAL ACRYL

These primers are also ideal to use to stabilize a loose or crumbly surface.

2. Application

Before use, lightly stir the content and apply it as it is or thinned with 5-10% clean water. Two coats of ISOMAT PROFESSIONAL ACRYL are applied with a roller, brush or airless gun. The second coat is applied after the first one has completely dried. Temperature during application and drying of the paint should be between +10°C and +35°C.

Coverage

ISOMAT PROFESSIONAL ACRYL covers 12 m²/l per coat, when applied on previously prepared surfaces.
(EN ISO 6504- 1).

Packaging

ISOMAT PROFESSIONAL ACRYL is supplied in 0.75 l, 3 l and 9 l containers.

Shelf life – Storage

24 months from production date if stored in original, unopened packaging, at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.

Volatile Organic Compounds (VOCs)

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory c, type WB is 40 g/l (2010) for the ready-to-use product.

The ready-to-use product ISOMAT PROFESSIONAL ACRYL contains a maximum of 40 g/l VOC.



2032

ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag Athanasios, Greece

16

2032-CPR-10.11

DoP No.: ISOMAT PROFESSIONAL ACRYL

/ 1427-03

EN 1504-2

Surface protection products

Coating

Permeability to CO₂: Sd > 50m

Water vapor permeability: Class I (permeable)

Capillary absorption: w < 0.1 kg/m²·h^{0.5}

Adhesion: ≥ 1.0 N/mm²

Artificial weathering: Passes

Dangerous substances comply with 5.3

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475

www.isomat.eu e-mail: info@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

