



HIGH TACK TURBO

A single component, moisture curing high viscosity elastomeric silane terminated sealant with INCREDIBLE tackiness. It cures to form a strong and highly flexible resistant joint with excellent adhesion on most substrates. **DYNA-FIX® High Tack Turbo** can be used indoor or outdoor and offers excellent adhesion on common substrates such as glass, metals, pre-lacquered aluminum, PVC, plastic, wood, polyester, stone, concrete etc. It is commonly used for bonding materials subjected to vibrations and movement.

Approvals



Features

- 3 Second Bond
- No primer required
- Strong adhesion
- Indoor & Outdoor Use
- Excellent UV and aging resistance properties
- Good resistance to vibrations
- No shrinkage, sagging nor stringing



WEATHER RESISTANT



MIRROR BONDING



NON STAINABLE



PAINTABLE



30KG/CM²



BONDS UNDERWATER



REMAINS ELASTIC



TEMP RESISTANCE

Surface Preparation

Surfaces must be clean, dry and free of grease, dust, oil and any contaminant to ensure that the bonding process is not compromised. Suitable solvents such as methylethylketone, acetone etc. may be used to clean surfaces.

Instructions

Apply strips 5 to 10 cm apart using either a manual or a pneumatic gun.
 No mechanical holding is required in general. For heavier elements, mechanical holding may be required before polymerization.
 Once the cartridge is opened, the product should be used within 24 hours otherwise, the product could harden.
 Do not apply at temperatures below 5°C.
 During curing, contact with non-cured polyurethanes should be avoided.

Technical Data

Property	Unit	Value
Skin over time (23°C / 50% RH)	Min	10
Density @ 20°C	g/ml	1.54
Temperature Resistance	°C	-40 to +90
Application Temperature	°C	+5 to +40
Shore A Hardness		65
Overall Appearance		Paste
Elongation at break (DIN 53504)	%	>325
Modulus at Maximum Force (DIN 53504)	MPa	1.8
Sagging		None
UV Resistance		Good
Water Resistance		Good




Shelf Life

18 months from date of production, when stored at or below 25°C in the original unopened container

Packaging

- 290 mL cartridge

Standard Colors



Designed & Manufactured According to AFAQ
 ISO 9001:2015 Certified Quality Management System

The information is offered in good faith and is believed to be accurate. It should not however be used in substitution for customer's tests to ensure that DYNA-FIX® products are safe, effective and compatible for the intended use. Sole warranty is that the product will meet the DYNA-FIX® sales specifications in effect at the time of delivery. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.